

Properties	Test Method	Unit	LIGHT WEIGHT MEDIUM					MEDIUM			
Grammage	ISO 536	gsm	70	75	80	85	90	100	110	120	
			$\pm 4 \%$								
Thickness	ISO 534	μm	110	120	125	135	140	160	170	180	
			$\pm 10 \%$								
CMT 30 min.	ISO 7263	N	85	90	95	110	125	130	143	156	
SCT CD min.	ISO 9895	kN/m	0,95	1,00	1,15	1,30	1,35	1,35	1,49	1,62	
Moisture	ISO 287	%	7,5 - 8,0								